

- **product name** : ELASTOM FE

- **general features**

1K enamel based on urethan- elastomeric- aliphatic resins. It is suitable for direct application on rigid and flexible PVC and PUR, on natural and on synthetic rubber.

Very fast drying

Suitable for outdoor

Against yellowing

- **use**

Direct application on rigid and flexible PVC and PUR, on natural and on synthetic rubber.

- **recommended cycles**

This product can be overcoated with paints of the same nature and with 2K paints.

- **application and thinning method**

spray : 40 - 80 % with X 123 or X485

immersion : with X 485

specific weight : min. 900 g/l - max. 1100 g/l

solid content : by weight = min. 19,5 % - max. 21,5 %
by volume = min. 16,0 % - max. 17,5 %

film appearance : semiglossy

color : on demand

number of components : 1

typical thickness : 5 – 10 micron

theor.coverage: min. 15,0 m²/l - max. 30,0 m²/l

drying at 25°C. :

dust free : 5 minutes

touch free : 40 - 50 minutes

depth : 3 hours

baking :

20 minutes at 60°C

overcoating time :

min. wet on wet - max. unlimited

shelf life : 12 months at + 5/35°C.